

PURA

**BIG SIZE
PORCELAIN
SLABS**





100% NATURAL
NO HARMFUL SUBSTANCES



HYGENIC
SUITABLE FOR FOOD CONTACT



SCRATCH-PROOF
RESISTANT TO USE AND ABRASION



EASY TO CLEAN
RESISTANT TO CONVENTIONAL CHEMICAL
DETERGENT



FROST RESISTANT
WEATHER RESISTANT



100% RECYCLABLE



RESISTANT TO HIGH TEMPERATURES
HEAT RESISTANT



WATERPROOF
ABSORPTION COEFFICIENT NEAR ZERO

TECHNICAL CHARACTERISTICS

PORCELAIN STONEWARE
CLASS UNI 14411 – Blā GL

FEATURES	UNIT OF MEASUREMENT	MEAN VALUE	REQUIRED STANDARDS	TEST METHOD
DIMENSIONS – LENGTH AND WIDTH	%	ACCORDING	+/- 0.6 MAX	UNI EN ISO 10545-2
SIDES STRAIGHTNESS	%	ACCORDING	+/- 0.5 MAX	UNI EN ISO 10545-2
SIDES ORTOGONALITY	%	ACCORDING	+/- 0.6 MAX	UNI EN ISO 10545-2
FLATNESS	%	ACCORDING	+/- 0.5 MAX	UNI EN ISO 10545-2
THICKNESS	%	ACCORDING	+/- 0.5 MAX FROM DECLARED VALUE	UNI EN ISO 10545-2
WATER ABSORPTION	%	ACCORDING	≤ 0.5	UNI EN ISO 10545-2
BREAKING STRENGTH	N	ACCORDING	≥ 700 FOR < 7,5 mm TH. ≥ 1300 FOR ≥ 7,5 mm TH.	UNI EN ISO 10545-2
MODULUS OF RUPTURE	N/mm ²	ACCORDING	≥ 35	UNI EN ISO 10545-2
COEFFICIENT OF LINEAR THERMAL EXPANSION	"MK (-1)	a7,00	DECLARED VALUE	UNI EN ISO 10545-2
RESISTANCE TO THERMAL SHOCK		RESISTS	PASS ACC. TO 10545-1	UNI EN ISO 10545-2
CHEMICAL RESISTANCE		ACCORDING	MINGB	UNI EN ISO 10545-2
RESISTANCE TO ACID AND LOW CONCENTRATION BASES		ULA	METHOD AVAILABLE	UNI EN ISO 10545-2
FROST RESISTANCE		RESISTS	PASS ACC. TO 10545-1	UNI EN ISO 10545-2
STAIN RESISTANCE		ACCORDING	MINIMUM CLASS 3	UNI EN ISO 10545-2
SURFACE HARDNESS		5-8	≥ 5	(EN 101)

PURA

CALACATTA PURA

FULL SLAB – 320 x 160 x 1.2 cm



2 BOOKMATCHED SLABS



DETAIL




PURA

STATUARIO PURA

FULL SLAB – 320 x 160 x 1.2 cm



2 BOOKMATCHED SLABS




DETAIL




DESIGNS AND FINISHINGS

POLISHED SURFACE




CALACATTA PURA "A"



CALACATTA PURA "B"



STATUARIO PURA "A"



STATUARIO PURA "B"

SILK SURFACE




CALACATTA PURA "A"



CALACATTA PURA "B"



STATUARIO PURA "A"



STATUARIO PURA "B"

PURA

Loc. Romagnano
37023 Grezzana (Vr) – ITALY

Office: +39 045 8650510

laponte@laponte.it

www.puraslabs.com